



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1809

Typical Characteristics

Refractive Index Liquid **Series A**
Refractive Index **1.56800** at 589.3 nm and 25 ° C

Composition Aliphatic / Alicyclic Hydrocarbons and Hydrogenated Terphenyl
Appearance Colorless to light yellow liquid
Odor Slight
Color Stability In Direct Sun: may slightly darken after 1 day, more after 4 months, dark after 6 years
Index Change Rate Low : -0.00002 to +0.00005
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.57010
Pour Point < -7 °C
Boiling Point > 262 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) >100 at 20°C
Density 0.999 g / cc at 25 °C
Density Temp Coef -0.0007 g / cc / °C
Coef of Thermal Expansion 0.0007 cc / cc / °C
Thermal Conductivity n/a cal / sec / cm² / °C - 1 cm thickness

Viscosity 80 cSt at 25 °C 80 cP at 25 °C
Surface Tension 36 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone, Ethanol

Insoluble Water

Compatible 10 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Silicone (Sylgard 184) and Fluorosilicone (730 RTV) Rubbers, Tygon F-4040-A, Tygothane; Aluminum, Brass, Copper, Steel

Incompatible Polystyrene, Latex, Neoprene, Silicone (3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series A**
 Refractive Index **1.56800** at 589.3 nm and 25 °C

Cauchy Coefficients
 A: 1.543565E+00
 B: 7.6259E+03
 C: 2.9857321E+08

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	-	-	-	-	-
240.0	-	-	-	-	-
250.0	-	-	-	-	-
270.0	-	-	-	-	-
290.0	-	-	-	-	-
308.0	-	-	-	-	-
355.0	1.623	73	4	0	0
365.0	1.618	96	66	2	0
406.0	1.6008	99	91	38	0
473.0	1.5836	100	99	89	32
532.0	1.5742	100	100	96	67
589.3	1.5680	100	100	98	82
632.8	1.5645	100	100	99	91
656.3	1.5629	100	100	100	95
790.0	1.5566	100	100	100	98
828.0	1.5553	100	100	100	99
981.0	1.552	100	100	97	77
1310.0	1.548	100	99	90	36
1550.0	1.547	100	98	85	19
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0183

Abbe v_D 31.0

Temp. Coefficient -0.000421 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening