



Cargille Laboratories
55 Commerce Rd - Cedar Grove, NJ 07009-1289
Phone : 973-239-6633 - Fax : 973-239-6096 - Web : www.cargille.com

Catalog # 1806

Typical Characteristics

Refractive Index Liquid **Series AA**
Refractive Index **1.40200** at 589.3 nm and 25 ° C

Composition Siloxane and Aliphatic / Alicyclic Hydrocarbons
Appearance Colorless Liquid
Odor None
Color Stability In Direct Sun: no visible change after 10 years
Index Change Rate Very Low : 0.00000 to +0.00001
by Evaporation expected after 32 days with exposed surface area to volume ratio of 0.2 cm²/cc @ 25 °C

Index at 20°C 1.40405
Pour Point < -7 °C
Boiling Point > 200 °C (760 mm Hg)
Flash Point > 138 °C (COC)
Brix Value (Per ICUMSA) 42.1 at 20°C
Density 0.927 g / cc at 25 °C
Density Temp Coef -0.0009 g / cc / °C
Coef of Thermal Expansion 0.0010 cc / cc / °C
Thermal Conductivity 0.0003 cal / sec / cm² / °C - 1 cm thickness

Viscosity 10 cSt at 25 °C 10 cP at 25 °C
Surface Tension 19 dynes/cm at 25 °C

Soluble Carbon Tetrachloride, Ethyl Ether, Heptane, Methylene Chloride, Naphtha, Toluene, Turpentine, Xylene

Partly Soluble Acetone

Insoluble Ethanol, Water

Compatible 1 Month Immersion at 25 °C : Acrylic, Cellulose Acetate, Epoxy, Mylar, Nylon, Polycarbonate, Polyester, Polyethylene, Polypropylene, Polystyrene, Polyurethane, Polyvinyl Chloride, Phenolic, Teflon, Neoprene and Fluorosilicone (Silastic 730 RTV) Rubbers ; Tygon F-4040-A, Tygothane, Aluminum, Brass, Copper, Steel

Incompatible Latex, Silicone (Sylgard 184 and 3140 RTV) Rubber, Tygon S-50-HL, R-3603, B-44-3



Refractive Index Liquid **Series AA**
 Refractive Index **1.40200** at 589.3 nm and 25 °C

Cauchy Coefficients
 A 1.389881E+00 B 4.3288E+03 C -4.1710444E+07

Cauchy Equation at 25°C $A + B / \lambda^2 + C / \lambda^4$ (λ = Wavelength in nm)

Wavelength (nm)	Refractive Index	Transmittance			
		0.1 mm	1 mm	1 cm	10 cm
225.0	1.46	97	77	8	0
240.0	1.45	99	91	39	0
250.0	1.45	99	92	42	0
270.0	1.44	99	95	58	0
290.0	1.44	100	98	78	8
308.0	1.43	100	99	91	37
355.0	1.422	100	100	99	90
365.0	1.420	100	100	100	98
406.0	1.4146	100	100	100	98
473.0	1.4084	100	100	100	99
532.0	1.4047	100	100	100	99
589.3	1.4020	100	100	100	99
632.8	1.4004	100	100	100	99
656.3	1.3997	100	100	100	99
790.0	1.3967	100	100	100	99
828.0	1.3961	100	100	99	91
981.0	1.394	100	100	98	82
1310.0	1.392	100	100	96	64
1550.0	1.392	100	96	64	1
2500.0	-	-	-	-	-
3700.0	-	-	-	-	-

($n_F - n_C$) 0.0077

Abbe v_D 51.9

Temp. Coefficient -0.000411 dn_D/dt (15 - 35 °C)

Shelf Life: 5 Years from Date of Manufacture for Unopened Bottles, Half the Remaining Time after Opening